



Comfort, Protection and Durability

Stedair® 3000^e is constructed of a hydro entangled, meta-aramid/para-aramid face fabric laminated to a bi-component polytetrafluoroethylene (PTFE) / polyurethane (PU) membrane matrix. The enhanced bi-component membrane is comprised of a hydrophilic (water loving) and oliophobic (oil hating) coating that is impregnated into the matrix providing improved adherence of seam tape. Additional testing includes Viral and Blood Borne Pathogen Resistance (ISO 16604/ASTM F1671/ASTM F1670).

- Para-aramid/Meta-aramid Durable Substrate
- PTFE Bi-Component Technology
- Weight : 145 g/m²
- Resistant to Blood Borne Pathogens
- Resistant to Viral Penetration
- Resistant to Common Chemicals

**STEDAIR® 3000^e IS COMPLIANT
TO EN469 , AS 4976 AND
OEKO-TEX® STANDARD 100**



Specification

CHARACTERISTICS	TEST METHOD	EN469 REQUIREMENT	STEDAIR® 3000E
6.1 Flame Spread**	EN ISO 15025:2016, procedure A	No afterglow No afterflame No occurrence of debris No formation of hole Mean afterflame <2 secs	No afterglow No occurrence of debris No formation of hole Afterflame = 0 secs
6.2 Heat Transfer (Flame) **	EN ISO 9151:2016	<div> <div>Level 1</div> <div>HTI24 ≥9.0</div> <div>Level 2</div> <div>HTI24 ≥13.0</div> <div>HTI24-12 ≥3.0</div> <div>(based on lowest result)</div> </div>	<div> <div>HTI24 ≥21</div> <div>HTI24-12 ≥6.0</div> <div>Level 2</div> </div>
6.3 Heat Transfer (Radiation) **	EN ISO 6942: 2002	<div> <div>Level 1</div> <div>RHTI24 ≥10.0</div> <div>Level 2</div> <div>RHTI24 ≥18.0</div> <div>RHTI24-12 ≥3.0</div> <div>≥4.0</div> <div>(based on lowest result)</div> </div>	<div> <div>RHTI24 ≥28</div> <div>RHTI24-12 ≥9.0</div> <div>Level 2</div> </div>
6.5 Heat Resistance	ISO 17493:2016 180°C for 5 mins	Materials shall not ignite or melt Shrinkage % < 5	No melt, drip, separation or ignition Shrinkage % = 0.4 L= 0.7 W= 0.2
6.9 Dimensional Change	EN ISO 13688:2013	Shrinkage % Max ± 3%	Shrinkage % L: -2.5% W: -1%
6.10 Resistance to penetration by liquid chemicals **	EN ISO 811:2018	No penetration to innermost surface. Repellency rate > 80%	<ol style="list-style-type: none"> 40% NaOH > 95% 36% HCl > 95% 30% H₂SO₄ > 95% 100% o-xylene >95% No penetration
6.11 Resistance to Water Penetration	EN ISO 811:2018	Level 1 < 20kPa Level 2 ≥ 20kPa	< 90 kPa ** Membrane side tested after 25 wash/dry cycles=<45kPa After heat = < 45kPa After Dry Cleaning = < 45kPa Level 2
6.11 Resistance to Water Penetration (SEAMS)	EN 20811: 1992 (1996)	Level 1 < 20kPa Level 2 ≥ 20kPa	< 20 kPa * testing complete at 20kPa
6.12 Water Vapour Resistance (Ret) **	EN ISO 11092:2014	Level 1 > 30m ² .Pa/W Level 2 ≤ 30m ² .Pa/W	Barrier Only = < 8 mm ² .Pa/W Composite = < 16 mm ² .Pa/W Additional testing after 25 washes = Composite = <18 m ² .Pa/W

ADDITIONAL STEDAIR® 3000^E TEST DATA ABOVE AND BEYOND STANDARD

Viral Penetration	ISO 16604	No visual penetration Assay Titer (PFU/mL) <1	Pass No visual penetration <1 PFU/mL
Blood Borne Pathogen Resistance + (SEAMS)	ASTM F 1671-07 NFPA 1971-2018 Resistance of materials used in Protective Clothing to Penetration by synthetic blood using PHI-X174 Bacteriophage	Exposure: 5 min @ 0 psig 1 min @ 2psig 54 min @ 0 psig Pass = No Penetration	Pass = No Penetration
Synthetic Blood Resistance	ASTM F 1670-98 NFPA 1971-2018 Resistance of materials used in Protective Clothing to Penetration by synthetic blood	Pass = No Penetration	Pass = No Penetration

** tested in composite form

