



Sted**AIR**  
**3000<sup>D</sup>**

# **Reliability You Can Trust. Durability When You Need It Most.**

Stedair® 3000<sup>D</sup> moisture barrier has a meta-aramid and para-aramid spun-lace substrate with silicone rubber dots laminated to a bi-component polytetrafluoroethylene (PTFE) /polyurethane (PU) membrane matrix. The PU is exposed to minimize seam movement and seam delamination.

Stedair® 3000<sup>D</sup> meets and exceeds the requirements of EN 469 Level 2 and is additionally certified to AS 4967.

---

## **PRODUCT BENEFITS:**

- PTFE Bi-component technology incorporating proprietary Silicone DOT system
- Certified blood borne pathogen and viral resistance (ISO 16604)
- Certified resistance to EN 469 and AS 4967 challenge chemicals
- Superior abrasion resistance
- Unmatched water vapour resistance (ISO 11092)



---

The information here is for non-binding, general information purposes only. Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Stedfast Inc. be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this document or the products to which the information refers. Stedfast Inc. makes no representations or warranties as to the completeness or accuracy of the information.

**Sted**AIR****®  
MOISTURE BARRIERS  
BY STEDFAST



StedAIR  
**3000<sup>D</sup>**



# Specification

CHARACTERISTICS	TEST METHOD	AS 4967 REQUIREMENT	STEDAIR® 3000D
Face Ignition**	ISO 15025(pa) After 5 wash-dry cycles	No specimen shall give hole formation No specimen shall give molten or flaming debris The mean value of the afterflame shall be ≤ 2s The mean value of the afterglow shall be ≤ 2s	No holes No molten or flaming debris 0.9s 0.3s
Heat Resistance	EN ISO 17493:2016 260°C for 5 mins After 5 wash-dry cycles	Materials shall not ignite or melt Shrinkage % < 5	No melt, drip, separation or ignition Shrinkage % = <1
Resistance to Water Penetration	EN ISO 811:2018 After 5 wash-dry cycles	≥ 200cm	>400cm
Dimensional Change	EN ISO 13688:2013 The assembly is washed and the shrinkage of each individual component is assessed	Shrinkage % Max ± 3%	Shrinkage % L: < 1 % W: <2 %
Heat Transfer (Flame) **	ISO 9151:1995	HTI24 ≥17s HTI24-12 ≥ 4s	HTI24 ≥18s HTI24-12 ≥ 5s
Heat Transfer (Radiant) **	ISO 6942:2002 Method B using a Heat Flux of 40kW/m <sup>2</sup>	t24 ≥22s t24-t12 ≥4s Mean T.F <60%	t24 ≥ 27s t24-t12 ≥ 8s Mean T.F ≤ 20%
Resistance to penetration by liquid chemicals **	EN ISO 6530:2005 1. 40% NaOH 2. 36% HCl 3. 30% H2SO4 4. 100% o-xylene	No penetration to innermost surface. Repellency rate > 80%	1. > 95 2. > 95 3. > 95 4. > 95 No penetration
Water Vapour Resistance (Ret) **	EN ISO 11092:2014	Level 1 > 30m <sup>2</sup> .Pa/W Level 2 ≤ 30m <sup>2</sup> .Pa/W	Barrier Only = < 8m <sup>2</sup> .Pa/W Composite = < 15m <sup>2</sup> .Pa/W

\*\* tested in composite form



230 St. Charles S.  
Granby, QC, J2G 3Y3  
Toll Free: (888) 673-8441

800 Mountain View Drive  
Piney Flats, TN, 37686  
Toll Free: (888) 673-8441

